

• TRUSTED QUALITY SINCE 1921 •

**RUST-OLEUM®****RUST-OLEUM®  
QUICK PREP 3 IN 1****DESCRIPTION AND USES**

Rust-Oleum® Quick Prep 3-IN-1 combines the three most important steps to properly prepare your concrete into one step. Proper surface preparation maximizes the durability and life of your coating. With Quick Prep, clean, degrease and etch in one easy step to allow for proper adhesion of coatings, paints and stains. Quick Prep saves you time and money while ensuring maximum adhesion for any concrete-coating project.

Ideal for use on bare concrete: garage floors, concrete driveways, carports, patios, walkways and pool decks.

**PRODUCT FEATURES**

- Clean, degrease and etch in one step
- Prepares bare concrete for proper adhesion of coatings, paints and stains
- Safe near glass

**PRODUCT**

| SKU    | DESCRIPTION |
|--------|-------------|
| 379741 | 3.78 L      |

**PRODUCT APPLICATION**

**READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT**

**SURFACE PREPARATION**

Newly poured concrete must cure for a minimum of 30 days prior to cleaning or coating. Sweep surface to remove dirt and dust. Spot treat heavy grease stains first with Quick Prep before applying to entire area.

**PRODUCT APPLICATION (cont.)****APPLICATION**

1. Wet down entire surface and squeegee the excess water off the surface.
2. Dispense Quick Prep from a plastic watering can in 3m x 3m (10 ft. x 10 ft.) sections.
3. Working in 3m x 3m (10 ft. x 10 ft.) sections, scrub thoroughly with a stiff bristle broom.
4. There will be no audible fizzing. After scrubbing the section thoroughly, rinse off solution with clean water and move to the next section. Product should not be allowed to dry on the surface. Mist the surface as necessary to keep wet until ready to rinse.
5. When all sections are completed, rinse 3 times with clean water and scrub with a stiff bristle brush while rinsing. This will ensure no product remains on the surface. The surface should feel rough, like 150 grit sandpaper and water should easily be absorbed into the concrete.
6. Allow the surface to dry completely before applying any coatings, paints, stains or sealers. A squeegee will aid in the removal of excess water.

**COVERAGE**

**For Garage Floors:** One gallon of ready to use formula covers about 23.2 m² (250 Sq. Ft.)

**For Patios, Driveways and Sidewalks, Etc.:** Mix gallon of Quick Prep with one gallon of water. 7.6 l (Two gallon) mixture will cover about 46.5 m² (500 Sq. Ft.)

**LIMITATIONS**

Do not apply to concrete that has already been sealed, painted or stained as it will not etch the concrete.

**CLEAN-UP & STORAGE**

Clean all application tools with water immediately after use. Keep product from freezing-do not store at temperatures below 10°C (50°F).

|   |  |                |
|---|--|----------------|
|   | <b>TECHNICAL DATA</b>                          | <b>ROC-230</b> |
| • TRUSTED QUALITY SINCE 1921 •<br> | <b>RUST-OLEUM®</b><br><b>QUICK PREP 3 IN 1</b> |                |

**PHYSICAL PROPERTIES**

|  |            | QUICK PREP 3 IN 1   |
|--|------------|---|
| Composition  |            | Organic acids and surfactant blend  |
| Pigment  |            | N/A   |
| Solvent  |            | Water   |
| Weight   | Per Gallon | 8.64 lbs.   |
|  | Per Liter  | 1.04 kg   |
| Solids   | By Weight  | 11%   |
|  | By Volume  | 8%  |
| Volatile Organic Compounds                         |            | 0 g/l   |
| Practical Coverage                                 |            | Up to 23.2 m <sup>2</sup> /3.78 L (250 sq. ft./gal.)<br>Coverage will vary depending on surface porosity and application method |
| Dry Times @ 25°C (77° F) and 50% Relative Humidity |            | Allow to dry for 24 hours before staining, sealing or coating   |
| Shelf Life   |            | 2 years   |
| Flash Point  |            | 93°C (>200°F)   |
| Safety Information                                 |            | For additional information, see SDS   |

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.