

RUST-OLEUM®

INSTAPATCH® ULTRA RAPID CURING CONCRETE REPAIR

DESCRIPTION AND USES

InstaPatch® is a two component, 100% solids polyurea crack repair compound. This ultra fast cure crack repair can be used at temperatures as low as -5°F (-20.5°C) and is suitable for traffic in 15 minutes

FEATURES

- Bonds well to a variety of substrates including concrete, wood, fiberglass, and asphalt
- Fast cure times, even in cold temperatures
- Return to service in 10-30 minutes
- Virtually no odor

PRODUCTS

SKU #	Description
276981	Gray (when cured, black in liquid form)
284595	Tile Red
288391	Tile Red (16 ounce kit)
288395	Gray (16 ounce kit)

PACKAGING

1 gallon kit containing both components Part A and Part B components are packaged in ½ gallon plastic containers. Kit yields one full gallon.

PRODUCT APPLICATION

SURFACE PREPARATION

New concrete must cure 30 days at 70°F (21°C) before repairs are made. Remove all dirt, grease, oil, salt or other contaminants by washing surface with Krud Kutter® Original Cleaner Degreaser, commercial detergent or other suitable cleaner. Rinse thoroughly with fresh, clean water. Remove all loose, unsound, or deteriorated concrete.

Small hairline cracks must be chased using a v-shaped diamond crack chasing blade on a hand held grinder. The crack should be opened to a minimum of ¼ inch wide. Any oil or grease that may have seeped into a crack and contaminated the edge of the concrete must be removed by grinding if washing is not sufficient. Use dry silica sand to fill deep cracks leaving a depth of ¼ inch down from the surface. The InstaPatch will soak into the silica and fortify the patch.

PRODUCT APPLICATION (cont.)

MIXING

Mix both components separately prior to combining. Pour out equal volumes of each component, then combine and mix together for 20-30 seconds. InstaPatch cures very quickly, so only mix up amounts that can be used within 5 minutes. Once mixed, InstaPatch is an easy flowing liquid. For some repairs, such as spalled areas or edge repair, dry silica sand can be added and mixed in to create a trowelable paste. Never use more than one part silica to one part activated liquid.

APPLICATION

InstaPatch is suitable for application temperature down to -5°F (-20.5°C). Within one minute of mixing, pour InstaPatch into the crack to be filled. Fill the crack to a slight excess and allow to cure. InstaPatch will cure in 10-15 minutes. Once cured, and the material cannot be indented by a thumbnail, the excess material can be removed by grinding to a flush surface.

NOTE: InstaPatch must be profiled by grinding or sanding if it is going to be topcoated.

THINNING

Not required.

CLEAN-UP

Methyl Ethyl Ketone (MEK).

PERFORMANCE CHARACTERISTICS

Tensile Strength (ASTM D412)	4,800
Compressive Strength (ASTM C109)	5,600
With silica added	6,200
Elongation (ASTM D412)	6-8%
Hardness, Durometer (ASTM D2240)	67-72 D
Abrasion Resistance (ASTM D4060)	
CS-17 Wheel, 1,000 g load, 1,000 cycles	20

**TECHNICAL DATA****INSTAPATCH®****PHYSICAL PROPERTIES**

Resin Type		Polyurea
Solids	By Weight	100%
	By Volume	100%
Mixing Ratio		1:1 base to activator by volume
Induction Period		None required
Working Time		5 minutes @77°F (25°C)
Pot Life		None. Pour out all material immediately after mixing
Estimated Coverage*		230 linear feet per activated gallon @ ¼" wide and ¼" deep
Dry Times @ 72° F and 50% Relative Humidity	Dry Hard	5-10 minutes
	Foot Traffic	10 minutes
	Vehicle Traffic	30 minutes
Shelf Life		2 year
Safety Information		See SDS

*Coverage rate is estimated and accounts for material lost when grinding away excess material for a smooth finish.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.