

STAIN**TECHNICAL DATA****VARATHANE®
WOOD GRAIN ENHANCER****DESCRIPTION AND USES**

Varathane® Wood Grain Enhancer accents the wood grain on bare or stained wood. It is designed to create a colour contrast on a variety of projects. This product works best on wood with a significant grain pattern such as red oak, white oak or ash.

Not for use on outdoor surfaces. For wood substrates only.

PRODUCTS

SKU	Description
317177	Enhanced White – 946mL
317179	Enhanced Black - 946mL

PRODUCT APPLICATION**SURFACE PREPARATION**

Start with bare wood. Use a clean rag dampened with water and wipe over the wood. Apply light pressure using a steel brush in the direction of the grain to open up the wood grain. Allow the surface to dry. Remove any dust with a clean, dry rag. **OPTIONAL:** Stain can be applied to add colour to the wood. For best results, use a Varathane stain.

APPLICATION

Stir material thoroughly before and occasionally during use. For best results use at temperature between 15°C - 32°C (60°F - 90°F). Apply Wood Grain Enhancer liberally to wood with a lint-free rag against the grain. Allow Wood Grain Enhancer to sit for 1-2 minutes. With a clean rag, wipe against the wood grain to wipe away excess material. Wood Grain Enhancer will sit in the grain and create your final look.

PROTECTING THE FINAL FINISH: To complete your project, and for the best protection, finish with any Varathane Clear Finish depending on your project needs. Clear Finish can be applied 2 hours after application of the Wood Grain Enhancer

COVERAGE

4.5 m² (50 ft²).

CLEAN UP

Soap and Water

REGULATORY

CAUTION: Use only in a well ventilated area. Do not breathe vapours. May irritate eyes and skin. Do not get in eyes, on skin or clothing. **KEEP OUT OF REACH OF CHILDREN.**

FIRST AID TREATMENT: If breathed in, move person to fresh air. If swallowed call Poison Control Centre or doctor immediately. Do not induce vomiting. If on skin, rinse well with water.

KEEP FROM FREEZING

DO NOT THIN. Not for use on outdoor surfaces. For Wood Substrates Only

**TECHNICAL DATA****VARATHANE® WOOD GRAIN ENHANCER****PHYSICAL PROPERTIES**

		WOOD GRAIN ENHANCER
Resin Type		Water Emulsifiable Modified Linseed Oil and Alkyd Resin
Pigment Type		Organic and Inorganic Pigments
Solvents		Propylene Glycol and Water
Weight	Per Gallon	8.32 lbs.
	Per Liter	1.00 kg
Solids	By Weight	20.3%
	By Volume	19.9%
Volatile Organic Compounds		<100 g/l (0.83 lbs./gal.)
Recommended Dry Film Thickness (DFT) Per Coat		Varies depending on wood type and porosity
Wet Film to Achieve DFT (unthinned material)		Varies depending on wood type and porosity
Practical Coverage at Recommended DFT (assumes 15% material loss)		Up to 25m ² (275 FT ²) per 946ml- depending on wood type and porosity
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	1 hour
	Recoat	2 hours
	Topcoat	2 hours
Shelf Life		3 years
Flash Point		>93°C (>200°F)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.