



EPOXYSHIELD® ASPHALT DEPRESSION FILLER & LEVELER

DESCRIPTION AND USES

EpoxyShield® Asphalt Depression Filler & Leveler is a ready-to-use, heavy-duty filler/leveler that combines flexibility and resiliency in a trowelable form. Use EpoxyShield Depression Filler & Leveler to fill cracks over 12 mm (½") in width, fill depressions left by parked automobiles or raise the surface of low areas in asphalt driveways.

PERFORMANCE CHARACTERISTICS

- Advanced formula
- Easy application
- Dries black

PRODUCTS

SKU	DESCRIPTION
258027	3.4 Litres
266286	10 Litres

PRODUCT APPLICATION

SURFACE PREPARATION

To ensure proper adhesion, make sure the entire driveway surface is free of dirt, debris, oil and grease spots. Sweep driveway with a stiff bristle broom. Trim any grass and weeds overgrowing onto the driveway. If grease, oil or chemical stains are present, clean thoroughly with EpoxyShield Spot Cleaner®, remove oil stains with EpoxyShield Oil Stain Remover following package instructions. For general cleaning, apply Krud Kutter, scrub with a stiff bristle broom, then hose off with fresh, clean water. Allow the surface to dry completely before application of sealer.

PRODUCT APPLICATION

APPLICATION

NOTE: Protective rubber gloves are recommended when using this product.

Use EpoxyShield Depression Filler & Leveler only when air, material, and surface temperatures are above 10°C (50°F) and no rain is forecast for 24 hours. For cracks over 12 mm (½") in width, apply sufficient Depression Filler & leveler to completely fill the crack using a trowel or spatula according to the size of the area to be repaired. Ensure that the surface is completely smooth before allowing the material to cure. For depressions or to raise low areas, work in layers of maximum 24 mm (1") thickness. Allow the material to set approximately 30 minutes, then add additional material to complete the project.

DRY & RECOAT TIMES

Dry times are based on 21°C (70°F). Allow for longer dry times at cooler temperatures. EpoxyShield Depression Filler & Leveler is ready for vehicular traffic or for sealing in 24 hours.

COVERAGE

One 3.4 litre container will fill an area of 35 cm² (3.8 sq. ft.) to a depth of 24 mm (1").

CLEAN UP

Wash tools and equipment with warm soap and water immediately after use. Use mineral spirits if the product has dried.

	TECHNICAL DATA	ESH-32
	EPOXYSHIELD® ASPHALT DEPRESSION FILLER & LEVELER	

PHYSICAL PROPERTIES

		ASPHALT DEPRESSION FILLER & LEVELER
Resin Type		Asphalt
Pigment Type		Mineral
Solvents		Water
Weight	Per Liter	1.15 kg
	Per Gallon	9.6 lbs.
Solids	By Weight	60.0%
	By Volume	54.0%
Volatile Organic Compounds		0 g/l
Practical Coverage (assumes 15% material loss)		Will fill an area of 35 cm ² (3.8 sq. ft.) to a depth of 24 mm (1")
Dry Times at 21-27°C (70-80°F) and 50% Relative Humidity	Touch	2 hours
	Recoat	4 hours
	Full Cure	24 hours
Shelf Life		1 year
Flash Point		>93°C (200°F)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary slightly from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.